

COMPLEX CHEMICAL CO, INC.

MGVI-200 SV

DESCRIPTION:

MGVI-200 SV IS A SOLUTION OF VERY SHEAR STABLE POLYMER DISSOLVED IN 100N PARAFIN OIL.

TYPICAL INSPECTIONS:

VISCOSITY CST @ 100°C	1400 - 1600
WEIGHT-LBS/GALLONS @ 60° F	7.08 - 7.21
SSI - KURT ORBHAN	4.0
*OIL BLEND VISCOSITY CST @ 100°C	15.0 - 17.0
COLOR	3 MAX
FLASH POINT F C.O.C.	170 C
APPEARANCE	CLEAR
*CONTROL BLEND	
MGVI-200 SV	10.0%
200 NEUTRAL OIL	90.0%

The viscosity of MGVI-200 SV is typically 1500 CST @ 100°C. It can vary, but each batch is controlled by the oil blend viscosity test for consistency.